



FAR EAST MAGNETICS

遠東磁鐵製品公司

Sintered Neodymium Iron Boron (NdFeB) Magnet

表面處理 Surface Treating									
Coating	Ni	Ni+Cu+Ni	Zn	Color Zn	Ni+Au	Epoxy	Ni+Sn	Multilayer Ni	Chemical Ni
Corrosive resistance	Good	Excellent	Good	Excellent	Good	Very good	Good	Excellent	Good
Colour	Silver	Silver	Matt Silver	Rainbow	Gold	Black	Dark Silver	Silver	Silver
Thickness (µm)	≥ 10	≥ 12	≥ 8	≥ 12	≥ 12	10-30	≥ 12	≥ 18	≥ 12
Salt Spray Test (hour)	≥ 24	≥ 48	≥ 24	≥ 48	≥ 36	≥ 108	≥ 36	≥ 168	≥ 96