

Plastic Bonded Ferrite Magnets

一般磁材性能 Typical Magnetic Properties				
牌號 Grade	性能 Properties			
	剩磁 Remanence (Br)	矯頑力 Coercivity (bHc)	內稟矯頑力 Intrinsic Coercivity (iHc)	最大磁能積 Max. Energy Product (BHmax)
	Gs	Oe	Oe	MGOe
PBF-7	1600	1400	1700	0.60
PBF-13	2500	2100	2950	1.50
PBF-15	2650	2200	2800	1.75
PBF-17	2850	2250	2700	2.00