

Bonded Ferrite Powder

一般磁材性能 Typical Magnetic Properties					
牌號 Grade	性能 Properties				
	剩磁 Remanence (Br)	矯頑力 Coercivity (bHc)	內稟矯頑力 Intrinsic Coercivity (iHc)	最大磁能積 Max. Energy Product (BHmax)	平均粒度 Average Particle Size
	Gs	Oe	Oe	MGOe	μm
FP-7S	1900	1350	1900	0.70	1.9-5.0
FP-10S	2150	1450	1800	1.05	1.1-1.5
FP-11S	2250	1550	1950	1.15	1.3-1.7
FP-256	2560±20	2300±50	3000±300	1.60±0.03	0.95-1.15
FP-261	2610±20	2450±50	3300±300	1.60±0.03	0.95-1.15
FP-266	2660±20	2550±50	3300±300	1.73±0.03	0.95-1.15
FP-270	2700±20	2600±50	3300±300	1.79±0.03	0.95-1.15