

### Magnetic Compound (Granulate) for production of Flexible Magnetic Rubber

一般磁材性能 Typical Magnetic Properties				
牌號 Grade	性能 Properties			
	剩磁 Remanence (Br)	矯頑力 Coercivity (bHc)	內稟矯頑力 Intrinsic Coercivity (iHc)	最大磁能積 Max. Energy Product (BHmax)
	Gs	Oe	Oe	MGOe
FEG-09	1800	1450	2100	0.70
FEG-10	2050	1700	2550	1.00
FEG-12	2400	2000	2800	1.40