

Bonded NdFeB Powder

一般磁材性能 Typical Magnetic Properties								
牌號 Grade	性能 Properties							
	剩磁 Remanence (Br)		矯頑力 Coercivity (bHc)		內稟矯頑力 Intrinsic Coercivity (iHc)		最大磁能積 Max. Energy Product (BHmax)	
	KGs	mT	KOe	KA/m	KOe	KA/m	MGOe	KJ/m ³
BNP-A	7.4-8.0	0.74-0.80	5.5-6.2	440-496	13.0-17.0	1035-1360	10.0-12.0	80-96
BNP-B	7.4-8.3	0.74-0.83	4.0-6.5	320-520	7.0-10.0	560-800	8.0-13.5	64-108
BNP-C	7.4-8.1	0.74-0.81	5.5-6.3	440-504	13.0-17.0	1035-1360	10.0-12.0	80-96
BNP-D	7.4-8.3	0.74-0.83	5.5-6.5	440-520	8.0-10.0	640-800	11.5-13.5	92-108
BNP-ES	8.5-11.0	0.85-1.10	2.4-3.5	192-280	3.0-5.0	240-400	7.0-9.5	56-76