

**Flexible NdFeB Rubber Magnet**

一般磁材性能 Typical Magnetic Properties										
牌號 Grade	性能 Properties									
	剩磁 Remanence (Br)		矯頑力 Coercivity (bHc)		內稟矯頑力 Intrinsic Coercivity (iHc)		最大磁能積 Max. Energy Product (BHmax)		最高工作溫度 Max. Oper. Temp.	密度 Density
	<i>mT</i>	<i>Gs</i>	<i>KA/m</i>	<i>Oe</i>	<i>KA/m</i>	<i>Oe</i>	<i>KJ/m<sup>3</sup></i>	<i>MGOe</i>	<i>°C</i>	<i>g/cm<sup>3</sup></i>
N2	250-350	2500-3500	120-200	1500-2500	150-320	2000-4000	12-20	1.5-2.5	≤ 120	3.30-3.90
N3	330-430	3300-4300	170-250	2100-3100	302-540	3800-6800	20-28	2.5-3.5	≤ 120	4.00-4.60
N4	380-480	3800-4800	210-300	2700-3700	540-700	6800-8800	28-36	3.5-4.5	≤ 120	4.40-5.00
N5	430-530	4300-5300	250-340	3200-4200	620-780	7800-9800	36-44	4.5-5.5	≤ 120	4.65-5.25
N6	480-580	4800-5800	290-380	3700-4700	630-800	8000-10000	44-52	5.5-6.5	≤ 120	4.65-5.25
N7	530-630	5300-6300	340-420	4300-5300	670-880	8500-11000	52-60	6.5-7.5	≤ 120	4.80-5.40
N8	570-670	5700-6700	350-440	4500-5500	670-880	8500-11000	60-68	7.5-8.5	≤ 120	5.10-5.70
N9	610-710	6100-7100	370-450	4700-5700	640-840	8000-10500	67-75	8.5-9.5	≤ 120	5.40-6.00